

# Recommendations For Handling Milliken Napery Fabrics

*For Laundries With Finishing Equipment*

## BASIC REQUIREMENTS:

1. Equipment **must** be free of burrs and sharp edges.
2. Washing equipment should have properly functioning water level and temperature controls.
3. Follow normal extraction procedures on cool (90°-100°F) linens. ■
4. Cleaning and waxing of ironer chest, and maintenance of roll pads and covers should comply with ironer manufacturer's recommendations. Maintain chest temperature between 315° F and 350° F on gas, steam, electric, and thermal fluid ironers.
5. Chemical feed systems must be functioning properly.

## PROCESSING REQUIREMENTS:

1. Before placing new linen into service it should be washed separately to remove manufacturing residual dyes. **Darker shades should be washed separately several times.**
2. Shade groups such as darks, mediums and lights should be washed separately. To avoid color contamination **red colors should always be washed separately.** Contact your Milliken representative for further information on shade groupings.
3. Milliken Napery Fabrics **should be washed separately** from 100% Cotton and Poly /Cotton blends **to avoid contamination** from lint and insure proper cleaning.
4. Wash formula and wash chemicals should be appropriate for type and amount of soil to be removed. ▼
5. Surfactants are recommended in the break cycle.
6. Use of complex phosphates along with silicated alkalis are recommended where permitted by law.
7. Soaps of animal or vegetable fats should be avoided.
8. Bleaches should not be used on colored Milliken napery.
9. White Milliken napery should receive antichlor treatment after hypochlorite or other chlorine bleaching.
10. For good mechanical action, load washwheel: Full Drop—90% Split Pocket—75% Y-Pocket—65%
11. Softeners and waxes must not be used with Milliken napery, as these will mask the absorbency of the fabric.
12. Adequate rinsing to remove residual chemicals is necessary to ensure maximum fabric life and color retention.

## PROCESSING REQUIREMENTS FOR GINGHAM CHECKS:

1. All requirements as stated above.
2. Checks must be washed separately from all other linen products to prevent color transfer from other products. Different colors of checks may be washed together after several washes.

■ Polyester Spun fabrics will retain more moisture and may require longer extract/drying time.

▼ Additional chemicals and/or time may be required for spun polyester.



**MILLIKEN®**  
Tablelinen Fabrics,  
Made in America

## SUGGESTED WASH FORMULAS & CHEMICAL SUPPLIES FOR MILLIKEN NAPERY

CYCLE	WATER LEVEL	°F TEMPERATURE	TIME (Min.)	SUPPLIES/100 lbs. POWDER SYSTEMS	SUPPLIES/100 lbs. LIQUID SYSTEMS
Flush	High	Split	3	-	-
Break	Low	160° *	12	1.5 - 2.5# Built Detergent	12-24 oz. Alkali
			▼	16-30oz. Surfactant (pH 11-11.5)	16-30oz. Surfactant (pH 11-11.5)
Carry-over	Low	160	6	-	-
●					
Rinse	High	145	2	-	-
Rinse	High	130	2	-	-
Rinse	High	115	2	-	-
Sour	Low	90 - 100	2	1-2 oz Sour/Do Not Drain After Sour (pH 5.5- 6.5)	1-2 oz Sour/Do Not Drain After Sour (pH 5.5- 6.5)
Starch Extract	Low	90 - 100	10	Add 3/4 to 1 1/2 lbs. Starch	Add 3/4 to 1 1/2 lbs. Starch
			■		

\* Temperatures lower than 160° F may require additional time and/or chemicals.

▼ Additional time and/or chemicals may be required for spun polyester.

● For white napery insert bleach cycle and antichlor in formula. Bleaching of colored napery is not recommended.

■ Polyester Spun Fabrics will retain more moisture and may require longer extract/drying time.

Time depends on machine design: experience shows that centrifugal time in minutes =  $1500 \div G \text{ force}$ . ( $G \text{ force} = \frac{\text{Basket RPM}^2 \times \text{DIA.}}{70,500}$ )

## STARCHING AND/OR SIZING OF MILLIKEN NAPERY

A clean fiber surface with good water absorbency is essential for proper starching or sizing of Milliken napery. To test quickly, place a few drops of water on a clean, ironed, cool, dry napkin. If water is completely absorbed into fabric within three (3) seconds, proper adhesion and film formation of starch or size should occur. Absorbency time in excess of three (3) seconds will require adequate clean up prior to starching or sizing.

1. Sour should be added to the wheel and allowed to dispense prior to adding starch or size. We suggest addition of sour **two (2) minutes** prior to addition of starch or size. this will help avoid differential absorption resulting in hard and soft spots in the napery. Sour should be added to achieve a ph of 5.5 to 6.5.
2. Starch or size should be applied during the sour step of the formula. Water level should be as low as practical (3" to 6" above basket). Water temperature should be maintained in the 90° F to 100° F range to facilitate dispersion and avoid highlighting.
3. Wheel should be allowed to run eight (8) to ten (10) minutes after addition of starch or size to allow even penetration of the dispersion throughout the load.
4. Twelve (12) to twenty-four (24) ounces per hundred weight of starch or combined starch and size are generally adequate to cover the range of aesthetics desired by restaurant customers. Corn, wheat and rice pregelatinized (dry to the wheel) starches as well as most cooked starches have all been found to work well on Milliken napery. Synthetic size in conjunction with starch also works well for those accounts who desire extra firmness. We suggest you contact your Milliken Technical Representative for assistance in selection and use of these products. Synthetic size must be removed with each wash.
5. If possible, use sufficient extraction to permit napery to be ironed without tumbling. Excessive tumbling will reduce the effectiveness of the starch or size significantly.

For additional information and assistance, contact:

Milliken & Company, Laundry Services

920 Milliken Road M-143

P.O. Box 1926

Spartanburg, SC 29304

1-800-322-Team (864) 503-2717

Your assurance of value, quality and performance.